

5-17-2011

Product Acceptance Criteria for Macro-Synthetic Fibers for Concrete Reinforcement, May 17, 2011

Maine Department of Transportation

Follow this and additional works at: https://digitalmaine.com/mdot_docs

Recommended Citation

Maine Department of Transportation, "Product Acceptance Criteria for Macro-Synthetic Fibers for Concrete Reinforcement, May 17, 2011" (2011). *Transportation Documents*. 2037.
https://digitalmaine.com/mdot_docs/2037

This Text is brought to you for free and open access by the Transportation at Digital Maine. It has been accepted for inclusion in Transportation Documents by an authorized administrator of Digital Maine. For more information, please contact statedocs@maine.gov.

**MAINE DEPARTMENT OF TRANSPORTATION
PRODUCT ACCEPTANCE CRITERIA FOR**

Macro-Synthetic Fibers for Concrete Reinforcement

General Description

This section includes the requirements for acceptance of macro-synthetic fibers which are permitted as a replacement for 6" x 6", #10 gauge welded wire fabrics reinforcement in the following selected precast concrete products:

Precast concrete manhole and catch basin units as allowed under MaineDOT Standard Specification, 712.06 Precast Concrete Units.

Requirements

The fiber manufacturer is required to obtain certified independent testing lab reports that confirm the product being submitted meets the requirements listed below and submit those results to the Maine Department of Transportation's Product Evaluation Committee.

1. Macro-synthetic fibers shall be manufactured from virgin polyolefins (polypropylene and polyethylene) and comply with ASTM C1116, *Type III Synthetic Fiber-Reinforced Concrete*. Fibers manufactured from materials other than polyolefins must show documentary evidence confirming their long term resistance to deterioration when in contact with the moisture and alkalis present in cement paste and the substances present in admixtures throughout the anticipated useful life of the structure.
2. The minimum fiber length required is 1.50 inches.
3. Macro-synthetic fibers have an aspect ratio (length divided by the equivalent diameter of the fiber) between 45 and 150.
4. Macro-synthetic fibers shall have a minimum tensile strength of 40 ksi when tested in accordance with ASTM D 3822.
5. Minimum dosage rate in pounds of fibers per cubic yard is established by determining an average residual strength of no less than 150 psi when tested in accordance with ASTM C1399. In all cases, ensure a minimum fiber dosage rate of 5 lbs/yd³ and a maximum fiber dosage rate of 10 lbs/yd³.
6. Macro-synthetic fibers shall have a minimum modulus of elasticity of 400 ksi when tested in accordance with ASTM D 3822.

Fibers meeting all of the above criteria will be pre-qualified for use and added to the Department's "Qualified Products List of Macro-Synthetic Fibers for Concrete Reinforcement."